

Uluslararası Alüminyum Standartları

ULUSLARARASI		ETİNORM	KANADA	FRANSA	ALMANYA		İTALYA	İNGİLTERE
(AA),ABD	ISO R209,TSE	ETİ		NF A02-004	DIN 1700	DIN 17007	UNI	BS, BS-L, DTD
1050A	Al99,5	ETİAL-5	1S	A-5	Al99,5	3.0255	4507	1B
1070A	Al99,7	ETİAL-7	99.70	A-7	Al99,7	3.0275	P-AIP 99,7	-
1080A	Al99,8	ETİAL-8	99.80	A-8	Al99,8	2.0285	P-AIP 99,8	1A
1200	Al99	ETİAL-I	2S	A-4	Al99	3.0205		1C
2017A	Al-Cu4Mg	ETİAL-22	17S	A-U4G	AlCuMg1	3.1325	P-AlCu4MnMg	H14
2024	Al-Cu4Mg1	ETİAL-24	24S	A-U4G1	AlCuMg2	3.1355	P-AlCu4,5MnMg	2L97/98
2117	Al-Cu2Mg		16S	A-U2G	AlCu2,5Mg0,5	3.1305		2L69
3003	Al-Mn1Cu	ETİAL-30	D3S	A-M1	AlMnCu	3.0517	P-AlMn1,2Cu	-
3004	-	ETİAL-31	4S; D4S	A-M1G	AlMn1Mg1	3.0526	AlMn1,2Mg	-
3103	Al-Mn1	ETİAL-33	3S	-	AlMn1	3.0515	3568	N3
3105	-	ETİAL-35	4S; D4S	-	AlMn0,5Mg0,5	3.0505		N31
5052	Al-Mg2,5	ETİAL-52	57S	-	AlMg2,5	3.3523	P-AlMg2,5	-
5056A	Al-Mg5		56S; A56S	-	AlMg5	3.3355		N6
5082	Al-Mg4		-	-	AlMg4,5	3.3345		-
5083	Al-Mg4,5Mn	ETİAL-58	D54S	A-G4,5MC	AlMg4,5Mn	3.3547		N8
5086	-		B54S	A-G4MC	AlMg4Mn	3.3545		N5/6
5251	Al-Mg2		M57S	A-G2M	AlMg2Mn0,3	3.3525		N4
5454	Al-Mg3Mn		B53S	A-G3MC	AlMg2,7Mn	3.3537		N51
5754	Al-Mg3	ETİAL-53	53S	A-G3M	AlMg3	3.3535	P-AlMg3,5	-
5182	Al-Mg5Mn				Al-Mg4,5Mn0,4			
6005A	Al-SiMg		51S	A-SG0,5	AlMgSi0,7	3.3210		H10
6060	Al-MgSi		50S	A-GS	AlMgSi0,5	3.3206		H9
6061	Al-Mg1SiCu	ETİAL-65	65S; CS5S	(6061)	AlMg1SiCu	3.3211	P-AlMg1SiCu	H20
6082	Al-Si1Mg	ETİAL-62	B51S	A-SGM0,7	AlMgSi1	3.2315	P-AlSiMgMn	H30
7020	Al-Zn4,5Mg1		D74S	A-Z5G	AlZn4,5Mg1	3.4335		-
7022	-		79S	A-Z4GU	AlZnMgCu0,5	3.4345		-
7075	Al-Zn6MgCu		75S	A-Z5GU	AlZnMgCu1,5	3.4365	P-AlZn5,5MgCu	2L95/96